

The detection of conformational disorder by thermal analysis

Bernhard Wunderlich

Oak Ridge National Laboratory and University of Tennessee
Department of Chemistry, University of Tennessee, Knoxville, Tennessee
37996-1600, U.S.A.

Abstract - Conformational disorder in crystals is found in many molecules that possess a plurality of conformational isomers. Typical examples are linear macromolecules such as polyethylene, polytetrafluoroethylene and trans-1,4-polybutadiene; and small molecules such as paraffins, cycloparaffins, soaps, lipids and many liquid-crystal forming molecules. Conformational motion is often coupled with the cooperative creation of disorder. In this case a heat and entropy of transition is observed by thermal analysis. Levels of transition entropies can be estimated, assuming most of the disorder can be traced to conformational isomerism. In case there is conformational disorder frozen-in at low temperature, thermal analysis can be used to find the glass transition of a condis crystal. An Advanced Thermal Analysis System has been developed, and will be described that permits a detailed interpretation of the thermal analysis traces. It rests with the establishment of high quality heat capacity for the rigid solid state (vibration only) and the mobile liquid state (vibrations and large amplitude cooperative motion).

THE TRANSITIONS BETWEEN MESOPHASES, CRYSTALS AND GLASSES

In a recent review of thermotropic mesophases and their transitions (ref. 1) it was suggested that crystals with dynamic conformational disorder do not fit into the standard classification of mesophases as either plastic crystals (ref. 2) or liquid crystals (ref. 3). At that time it was proposed that a distinct third type of mesophase exists, that of the condis crystal (with dynamic conformational disorder and long-range positional and orientational order). Figure 1 illustrates schematically the various condensed phases and




Fig. 1. Schematic diagram of the relationship between the three limiting phases (in double outline) and the six mesophases.

their interrelations. The three classical condensed phases: glass, crystal and melt, are outlined doubly. Glasses and crystals are solids, the melt is a liquid. Condis crystal, plastic crystal, and liquid crystal are increasingly less solid (more liquid). The arrows on the right-hand side indicate the possible transitions between the phases that are often first order transitions, i.e. transitions that involve a discontinuity in the first derivative of the Gibbs energy function, the entropy (ref. 4).

The overall entropy of fusion of a crystal, ΔS_f can be approximately separated into the three contributions arising from positional disordering, ΔS_{pos} , orientational disordering, ΔS_{orient} , and conformational disordering, ΔS_{conf} , so that

$$\Delta S_f = \Delta S_{pos} + \Delta S_{orient} + \Delta S_{conf}. \quad (1)$$

It is possible to make a first judgment of a phase classification based on the thermal analysis of the first order transitions. Such analysis is helped by the empirical "rules" that ΔS_{pos} is generally 7-14 J/(K mol) (Richards's rule) (ref. 5), ΔS_{orient} is usually 20-50 J/(K mol) (based on Walden's rule) (ref. 6), and ΔS_{conf} is about 7-12 J/(K mol) (ref. 7). While ΔS_{pos} and ΔS_{orient} are referred to the whole molecule, i.e. they do not change with size; ΔS_{conf} is referred to a flexible bond (or a rigid bead), i.e. for a molecule, ΔS_{conf} is size-dependent. The rather broad ranges of values indicate the approximate nature of this description. For a more precise analysis, effects of disorder, volume change, changes in vibrational frequency etc. would have to be detailed. Nevertheless, the empirical rules permit estimations of the various transition entropies corresponding to the arrows of the right-hand side of Fig. 1. Particularly well obeyed is a transition entropy of 7-14 J/(K mol) for the transition from the plastic crystal to the melt (ref. 2). The analogous transitions from the liquid crystalline phase to the melt are always much less than ΔS_{orient} , indicative of the rather high degree of orientational disorder and mobility in liquid crystals (ref. 1). Condis crystals, finally, are expected to show variable entropies of transition from the crystal to the condis-crystal and from the condis-crystal to the isotropic melt, depending on the type and concentration of conformational disorder.

On cooling, the mesophases do not always follow the equilibrium path. If the ordering to the crystal can be by-passed, the liquid-like cooperative motion of the mesophases freezes at a glass transition, as is indicated on the left side of Fig. 1. At these glass transitions there is no change in order and, as a result, no change in entropy. Since the liquid-like motion changes at the transition to practically only vibrational motion, there is a drop in heat capacity on vitrification. For liquid crystals, the existence of the glassy state was already implied in the work of Vorlaender (ref. 8). Their drop in heat capacity is practically identical to those for liquids (ref. 1). For plastic crystals, the glassy state was first recognized by Adachi, Suga, and Seki (ref. 9). The order of magnitude of the change in heat capacity at the glass transition of plastic crystals is also not much different from that of liquids. For the typical glass transition of a liquid it was found that the change in heat capacity is approximately 10-20 J/(K mol) when calculated per mole of mobile parts (beads) within the molecule (ref. 10). Since condis crystals show usually intermediate heat capacities between the solid and liquid states, their change in heat capacity on vitrification is expected to be variable also.

It seems reasonable, and has been illustrated on several examples, that molecules with dynamic conformational disorder in the liquid state show such conformational disorder also in the liquid crystalline and plastic crystalline states (ref. 11). The major need in distinguishing condis crystals from other mesophases is thus the identification of translational motion and positional disorder of the molecular centers of gravity in the case of liquid crystals, and of molecular rotation in the case of plastic crystals.

JUSTIFICATION OF THE EMPIRICAL ENTROPY DESCRIPTION

To find an explanation for Richards's rule one may postulate that the liquid state possesses a short-range "quasi-crystalline" structure (ref. 12). As the temperature increases, this structure changes gradually, to become "quasi-gaseous" close to the critical temperature (ref. 12). The melting process may be, based on this model, broken into three major steps. First, the crystal lattice is expanded to give the average separation of the motifs as it exists in the melt. Next, the motifs are dynamically disordered. Last, defects are introduced into the quasi-crystalline melt. Starting from a cubic close-packed crystal Lennard-Jones and Devonshire computed the three melting stages assuming interstitial atoms as defects (ref. 13). For Argon an entropy of fusion of 1.70 R, or 14.1 J/(K mol), was computed that matches the experimental equilibrium value of 14.0 J/(K mol) at 83.8 K. The entropy increase in going from fixed motifs in the small volume element of the crystal to the total volume of the melt (communal entropy) was earlier found to be R, or 8.31 J/(K mol) (ref. 14). The lower and upper limit of Richards's rule seem thus reasonable.

In analogy to the estimates of ΔS_{pos} , it is possible to suggest that the empirically observed values for ΔS_{conf} can be linked to the commonly used "rotational isomeric states" model of linear macromolecules (refs. 15-17). Assuming two to four rotational isomers to become dynamically accessible on a disordering transition and 75% of the total entropy change to be conformational, one expects an entropy gain of 7.7 to 15.3 J/(K mol), the correct size range of the experimental values. On the basis of atomistic calculations, a detailed rotator model was analyzed for the condis phase of flexible linear macromolecules using a cooperative statistical treatment (ref. 18). Both, the transition from the crystal to the condis crystal and from the condis crystal to the melt could be described

quantitatively for polyethylene and for trans-1,4-polybutadiene as a function of pressure. The overall melting of macromolecules was treated as an, at least, two-step transition: a conformational transition and the cooperative formation of dislocations, the latter giving rise to only minor changes in conformation (refs. 19,20). For the condensation states of polyethylene and possibly also trans-1,4-polybutadiene the two steps occur largely separated at the two equilibrium transition temperatures T_d and T_i (disordering and isotropization temperatures, respectively).

The orientational entropy of fusion $\Delta S_{\text{orient}} = 20\text{-}50 \text{ J}/(\text{K mol})$ is based on Walden's empirical rule of entropies of irregular, rigid molecules (ref. 6). Subtraction of the appropriate ΔS_{pos} leads to the suggested values. The separation of ΔS_{pos} and ΔS_{orient} is well documented by the plastic crystals that often show ΔS_{pos} as the isotropization transition (ref. 2).

CORRELATION BETWEEN MOTION AND HEAT CAPACITY

The major motion type for the crystalline and glassy solid states is vibration. For linear macromolecules one finds large deviations from the classical Einstein (ref. 21) or Debye (ref. 22) treatments of the heat capacity. Also, an early attempt to approximate the heat capacities with a combination of a 1-dimensional and 3-dimensional continuum to account for the anisotropy of the chain molecules (ref. 23) was by itself not applicable over a wide temperature range. The method that was finally successful (refs. 24,25) involves an approximation of the frequency spectrum by separation of the high-frequency group vibrations from the skeletal chain-vibrations. The group vibrations are then accessible from normal-mode calculations on isolated chains and are even transferable for polymers of similar chemical structure. The skeletal vibrations can then be approximated using the two-parameter Tarasov approach (θ_1 and θ_3) (ref. 23). Agreement between computation and experiment has been tested for almost 100 polymers and is usually better than $\pm 5\%$ over the whole temperature range, starting from about 10 K (refs. 26,27). Figure 2 illustrates the computed heat capacities of polystyrene, a polymer with six skeletal vibrations and 48 group vibrations per repeating unit. Within the small scale of the drawing there is hardly any difference between experiment (circles) and computation for the solid heat capacity (A skeletal contributions, B group vibration contributions, C total)(ref. 28).

Also plotted in Fig. 2 is the experimental heat capacity of the liquid (at constant pressure, curve E) (ref. 28). In simple cases, such as polyethylene, the heat capacity of the liquid state could be understood by introducing a heat capacity contribution for the excess volume (hole theory) and by assuming that the torsional skeletal vibration can be treated as a hindered rotator (ref. 29). A more general treatment makes use of a separation of the partition function into the vibrational part (approximated for heat capacity by the spectrum of the solid), a conformational part (approximated by the usual conformational statistics) (refs. 15-17), and an external or configurational part. The latter was shown to be almost completely represented by the difference of heat capacity at constant pressure and volume (ref. 30). The heat capacity of all polymers is thus understood well within the precision-range of the experiment.

Adding the measured heats of transition to the integrated heat capacities, it is then possible to compute not only enthalpies, but also absolute entropies and free enthalpies. The change in entropy with temperature and state of matter is illustrated in Fig. 3 for the




Fig. 2. Heat capacity of polystyrene.

- A: Contribution of the skeletal vibrations.
- B: Contribution of the group vibrations.
- C: Total heat capacity at constant volume.
- D: Experimental heat capacity at constant pressure.
- E: Heat capacity of the liquid.




Fig. 3. Entropy of cis and trans 1,4-polybutadiene.

example of 1,4-polybutadienes (ref. 31). The vibrational contributions to the entropies of the two isomers differ only little ($\theta_1 = 589$ K for the cis-isomer and 599 K for the trans-isomer). The sum of the entropies of the two stages of fusion of the trans-isomer are close to the single-step entropy of fusion of the cis-isomer. Typical is also the much larger accumulated vibrational entropy when compared to the transition entropy.

In the course of analysis of motion types in crystals and mesophases, it became clear that large scale motion is also possible in molecular crystals. Conformational, rotational, and even diffusional motion can start considerably below the melting or disordering transition temperatures. The major tools for the determination of this motion, commonly connected only with the liquid or mesophase, are the various forms of solid state NMR (ref. 32). In order not to lead to dynamic disorder, these larger scale motions must be jump-motions between positions of identical symmetry within the crystal. Since the intermediate in a jump-motion is present only during a negligible fraction of the total time, it can hardly be determined by most structure-analysis techniques such as X-ray diffraction and Raman or infrared spectroscopy. Similarly, there are hardly any effects thermodynamically as long as the order (entropy) sees little change (ref. 33). The changes in heat capacity when a torsional oscillator changes to a hindered rotator, for example, are gradual and occur usually over a temperature range of several hundred kelvins so that its initial jumping from minimum to minimum in potential energy is difficult to distinguish from a pure oscillator (refs. 25,29). Ultimately this motion leads always to disordering of the crystal to mesophases or the melt.

Another large amplitude molecular motion type, first analyzed in the gas phase of pentane (ref. 34) is the pseudorotation (ref. 35). It is an internal motion by changing mainly torsional angles of the nuclei which interconverts conformers that are identical except for the numbering of the atoms. To visualize the motion, one may start for cyclopentane, for example, with the molecule in the planar C_5 symmetry. This symmetry represents a local maximum in potential energy. There are then 10 puckered conformers of C_5 symmetry and 10 twisted conformers of C_2 symmetry, both types having almost the same low potential energy. Interchange within a group of isomeric conformers appears as a rotation about the axis normal to the plane of the molecule due to the indistinguishable nature of the CH_2 -groups, has, however, no momentum about this axis. The motion actually consists of displacements parallel to the pseudorotation axis of corresponding groups by rotational motion about bonds.

In the crystal, pseudorotation is strongly hindered at sufficiently low temperature because of the volume restrictions resulting from the closely packed structure. On changing to the plastic crystal phase this restriction is removed and pseudorotation is possible as in the liquid state. Larger cycloalkanes do not display a plastic crystalline state because of their larger deviation from a spherical shape. Still, these molecules show fast conformational interchange below any disordering transition temperature. This conformational interchange must occur largely within the confines of the corrugated, tubular volume available for the molecule within the crystal. Motion restricted to such a geometry can only be a concerted rotation and pseudorotation. The molecule must in this case reptate (ref. 36) along a corrugated circular path. To distinguish this type of motion from true rotation and pseudorotation we call it "rotoreptation". As in true rotations one expects no entropy gain in rotoreptation if the motion consists of jumps between positions of identical symmetry. In this case one would not detect structure changes in the crystal.

SUMMARY

Based on Advanced Thermal Analysis (ATHAS) it is possible to have considerable characterization of mesophases in general, and conformational disorder, in particular. Combining thermal analysis with microscopic analysis techniques like X-ray diffraction or solid state NMR permits complete characterization.

Acknowledgements

Much of this work was supported by the Polymers Program of the U.S. National Science Foundation (Grant Number DMR 83-17097). At ORNL funding was provided by the Division of Materials Science, Office of Basic Energy Sciences, U.S. Department of Energy, contract DE-AC05-84OR21400 with the Martin Marietta Energy Systems, Inc. A full report with detailed examples has been prepared during sabbatic stay in Germany supported by the Alexander von Humboldt Foundation 1987/88, and has been published in the *Adv. Polymer Sci.*, **87**, 1 1988.

REFERENCES

1. B. Wunderlich and Grebowicz, *J. Adv. Polymer Sci.*, **60/61**, 1 (1984).
2. see for example: Sherwood, N. ed. "The Plastically Crystalline State. (Orientationally-disordered crystals)." J. Wiley and Sons, Chichester 1979.

3. see for example: Gray, G. W. "Molecular Structure and the Properties of Liquid Crystals." Academic Press, New York 1962.
4. P. Ehrenfest, Acad. Sci., Amsterdam **36**, 153 (1933); Suppl. 75b, Mitt. Kammerlingh Onnes Inst., Leiden.
5. J. W. Richards, Chem. News **75**, 278 (1897).
6. P. Z. Walden, Elektrochem. **14**, 713 (1908).
7. B. Wunderlich, Macromolecular Physics, **3**, Crystal Melting. Academic Press, New York, 1980.
8. D. Vorlaender, Trans. Farad Soc. **29**, 207 (1933).
9. K. Adachi, H. Suga, and S. Seki, Bull. Chem. Soc. Japan **43**, 1916 (1970).
10. B. Wunderlich, J. Phys. Chem. **64**, 1052 (1960). The upper limit in ΔC_p applies for larger mobile parts in molecules, see B. Wunderlich and U. Gaur, Pure Appl. Chem. **52**, 445 (1980).
11. B. Wunderlich, M. Möller and H. G. Wiedemann, Mol. Cryst. Liq. Cryst., **140**, 211, 219, 231 (1986).
12. see for example: A. R. Ubbelohde, Melting and Crystal Structure. Oxford Univ. Press (Clarendon) London 1965; and The Molten State of Matter. Melting and Crystal Structure, Wiley, New York, 1978.
13. J. E. Lennard-Jones, A. F. Devonshire Proc. Roy. Soc. London, Ser. A **169**, 317; **170**, 464 (1939). See also J. deBoer, Theories of the Liquid State. Proc. Roy. Soc. London, Ser. A **215**, 1, (1952).
14. J. Hirschfelder, D. Stevenson, and H. J. Eyring, Chem. Phys. **5**, 896 (1937).
15. P. J. Flory, Structural Mechanics of Chain Molecules, Wiley (Interscience), New York, 1969.
16. T. M. Birshtein and O. B. Ptitsyn, Conformations of Macromolecules (translated from the Russian by S. N. Timasheff and M. J. Timasheff) Wiley (Interscience), New York, 1966.
17. M. V. Volkenstein, Configurational Statistics of Polymeric Chains (Translated from the Russian by M. J. Timasheff and M. J. Timasheff) Wiley (Interscience), New York, 1963.
18. H. P. Grossmann and W. R. Pechhold, Colloid and Polymer Sci., **264**, 415 (1986).
19. W. Pechhold, E. Liska, H. P. Grossman, P. C. Hägele, Pure Appl. Chem. **46**, 127 (1976).
20. W. Pechhold, H. P. Grossmann and W. v. Soden, Colloid and Polym. Sci. **260**, 248 (1982). 21. A. Einstein, Ann. Physik, **22**, 180 (1907), for correction see Ann. Physik **22**, 800 (1907).
22. P. Debye, Ann. Physik, **39**, 789 (1912).
23. V. V. Tarasov, Compt. Rend. Acad. Sci. URSS **46**, 110 (1945); **54**, 795 (1946); see also Zh. Fiz. Khim. **24**, 111 (1950); **27**, 1430 (1953).
24. B. Wunderlich, J. Chem. Phys. **37**, 1207 (1962).
25. B. Wunderlich, and H. Baur, Adv. Polymer Sci., **7**, 151 (1970).
26. for a recent summary see: B. Wunderlich and S. Z. D. Cheng, Gazz. Chim. Italiana, **116**, 345 (1986).
27. for an overall assessment see: H. S. Bu, S. Z. D. Cheng, and B. Wunderlich, J. Phys. Chem., **91**, 4179 (1987).
28. L. Judovits, R. C. Bopp, U. Gaur and B. Wunderlich, Polymer Phys. Ed. **24**, 2725 (1986).
29. B. Wunderlich, J. Chem. Phys. **37**, 2429 (1962); see also J. Polymer Sci., Part C, **1**, 41 (1963).
30. K. Loufakis, and B. Wunderlich, J. Phys. Chem., **92**, 4205 (1988).
31. J. Grebowicz, W. Aycock, and B. Wunderlich, Polymer, **27**, 575 (1986).
32. see for example: C. A. Fyfe, Solid State NMR for Chemists. CFC Press, Guelph, 1983.
33. I. Darmon, and C. Brot Mol. Cryst. **2**, 301 (1967): see also C. Brot and B. Lassier-Govers, Ber. Bunsen Ges. **80**, 31 (1976).
34. J. E. Kilpatrick, K. S. Pitzer, and R. J. Spitzer, Am. Chem. Soc. **69**, 2483 (1947), see also K. W. Pitzer, and W. E. Donath, J. Am. Chem. Soc. **81**, 3213 (1959).
35. see for example the reviews: H. L. Strauss, Ann. Rev. Phys. Chem., **34**, 301 (1983); L. A. Carriera, R. C. Lord, and T. B. Mallory, Jr., Top Curr. Chem., **82**, 1 (1979); A. C. Legon, Chem. Rev. 231 (1980).
36. P. G. DeGennes, J. Chem. Phys. **55**, 572 (1971).